

cod. COPY80

Parameters	Standard	Unit	Measurement
Substance	ISO 536	g/m ²	80 +/- 3%
Thickness	ISO 534	µm	105 +/- 4
Bulk	ISO 534		1,31
Moisture Content	ISO 287	%	4,2 +/- 0,5
Roughness	ISO 8791	Bendtsen ml/min	200 +/- 50
Whiteness	ISO 11475	CIE	161 +/- 3
Opacity	ISO 2471	%	91 +/- 2
Stiffness MD	ISO 2493	m/N	110 +/- 10
Stiffness CD	ISO 2493	m/N	45 +/- 5



References:
 Product is made taking into account requirements of DIN EN 12281
 Product made from ECF Pulp
 ISO 18001 - OHSAS Health & Safety

Technical Data Sheet

Production sites:

The production mills operate
 in compliance with the following
 standards



Special Attributes:

